



中国认2020-003272
国际互认
检测
TESTING
CNAS L0230



检 测 报 告

TEST REPORT

BETC-HJ-2020-P-00574

样品名称: 维护者隔热涂料

委托单位: 维护者新材料（厦门）有限公司

检测类别: 委托检验

国家化学建筑材料测试中心(建工测试部)
CHINA NATIONAL CENTER FOR TEST OF CHEMICAL BUILDING MATERIALS

国家化学建筑材料测试中心（建工测试部）



检测报告

委托编号 (Commission No.): 2020-003272

报告编号 (No. of Report): BETC-HJ-2020-P-00574

第1页 共2页 (Page 1 of 2)

样品名称	维护者隔热涂料	样品编号	HJ-2020-P-00574
委托单位	维护者新材料（厦门）有限公司	规格	MT/MB
		商标	维护者/WELLHOOD
生产单位	维护者新材料（厦门）有限公司	检测类别	委托检验
抽样单位	-----	样品数量	1kg
抽样地点	-----	抽样日期	-----
抽样基数	-----	到样日期	2020-06-02
样品批号	-----	送(抽)样人	刘海生
检测项目	高亮度产品：太阳光反射比、近红外反射比、半球反射率、污染后太阳光反射比变化率		
检测依据	JG/T 235-2014《建筑反射隔热涂料》 GB/T 9780-2013《建筑涂料涂层耐沾污性试验方法》		
判定依据	JG/T 235-2014《建筑反射隔热涂料》		
检测结论	经检测，该样品所检项目的检测结果达到JG/T 235-2014《建筑反射隔热涂料》表1高亮度产品的技术指标要求。 (本页以下无正文)		
仪器	辐射率仪、半球发射率标准片		
备注	-----		

批准：

批准人：[Signature]

审核：

审核人：[Signature]

主检：

主检人：姜广明

国家化学建筑材料测试中心 (建工测试部)

检测报告

委托编号(Commission No.):2020-003272

报告编号(No. of Report):BETC-HJ-2020-P-00574

第 2 页 共 2 页 (Page 2 of 2)

样品名称		维护者隔热涂料		样品编号		HJ-2020-P-00574		
检测条件		室温: (23±2)℃; 相对湿度: (50±5)%			报告日期		2020-06-16	
序号	检测项目		技术指标		检测结果			单项评定
JG/T 235-2014《建筑控温隔热热反射涂料》高光度产品 (L*=99)								
1	太阳光反射比		高光度≥0.65		0.89			符合
2	近红外反射比		高光度≥0.80		0.89			符合
3	半球发射率		≥0.85		0.89			符合
4	污染后太阳光反射比变化率		高光度≤20%		20%			符合
(以下空白)								
备注								
检测项目 1、2、4 项由国家化学建筑材料测试中心（建工测试部）的法人单位中国建筑科学研究院有限公司检测（资质认定证书编号：180001283476）。								

注 意 事 项

NOTICE

1. 报告无“检测测试专用章”或检测单位公章无效;

Test report is invalid without the “Stamp of test report” or that of test department on it.

2. 复制报告未重新加盖“检测测试专用章”或检测单位公章无效;

Duplication of test report is invalid without the “Stamp of test report” or that of test department re-stamped on it.

3. 报告无主检、审核、批准签字无效;

Test report is invalid without the signatures of the persons for chief test, verification and approval.

4. 报告涂改无效;

Test report is invalid if altered.

5. 对检测报告若有异议, 应于收到报告之日起十五日内向检测单位提出;

Different opinions about test report should be reported to the test department within 15 days from the date of receiving the test report.

6. 一般情况, 委托检测仅对来样负责, 样品信息由委托方提供。

In general, for entrusted tests the responsibilities are undertaken for the delivered samples only and the sample information is provided by clients.

地址: 北京市朝阳区北三环东路30号

ADD: NO.30, Beisanhuan East Road, Chaoyang District, Beijing, China

电话(Tel): 010-64517787 010-84281338

投诉电话: 010-64517830

传真(Fax): 010-84288515 010-84281338

邮政编码(Post code): 100013

Internet: <http://www.cabr-betc.com>